

## PLEXTOL B 500

PLEXTOL B 500 is an aqueous dispersion of a nonionic stabilized thermoplastic acrylic polymer.



For further information regarding this product please refer to:  
**Zieglerova, Jeaneta**

Tel: +420 737 206 966

eMail: Jeaneta.Zieglerova@synthomer.com

Property	Value	Unit	Method*
Solids Content	50	%	ISO 3251
pH Value	9.5		ISO 976
Viscosity	2500	Pa s	ISO 1652
Glass Transition Temperature	9	°C	
Density	1.07	g/cm <sup>3</sup>	
Mean Particle Size	0.15	µm	
Minimum Film-Forming Temperature	7	°C	
Surface Tension	40	mN/m	
Water Absorption (24h)	15	%	
Tensile Strength	3	N/mm <sup>2</sup>	
Elongation at Break	500	%	

<sup>1</sup> internal method based upon the specified norm

### Application Advice & Processing

PLEXTOL B 500 is preserved against bacterial and fungal attack. In the manufacture of finished products, the material has to be retreated, as usual, with suitable biocides to give enhanced preservation.

Film properties: Evaporation of the water above the minimum film-forming temperature leaves a transparent, cloudy film which is soft, extensible and slightly tacky at room temperature. - By mixing PLEXTOL B 500 with other emulsions from the PLEXTOL range, the film properties of the former can be influenced within wide limits and thus adapted to the intended application.

### Shipping and Storage

PLEXTOL B 500 is supplied in road tankers or in non-returnable plastics drums secured by a lid with clamping ring or in non-returnable palletized bulk containers (net weight 1,100 kg). PLEXTOL B 500 has to be stored protected from frost and, as far as possible, below 40 °C. Storage at temperatures between + 5 and + 30 °C is recommendable. PLEXTOL B 500 contains a preservative to counter microbial attack during transportation. To protect it against germination during subsequent storage, absolutely stringent plant hygiene and, under certain circumstances, the addition of suitable preservatives will be necessary. Care must be taken to ensure that drums and storage containers are tightly closed. During processing, storage and transport of the product contact with metals unprotected against corrosion (likewise non-ferrous metals) has to be avoided. When stored correctly PLEXTOL B 500 has a storage life of 12 months from date of delivery.

### Product Safety

Revision: 10/2014  
Before handling, please read the Safety Data Sheet of this product for advice on safety, use and disposal.

Disclaimer: This information and any other advice or recommendations given or made by us (collectively "Information"), are provided in good faith and are not intended to, nor do they, constitute professional advice or services. Information is provided "AS IS" and on an "AS AVAILABLE" basis and without warranty. We do not warrant or accept responsibility for the accuracy, timeliness or completeness of the Information, or for the suitability of the Information for a particular purpose. We do not accept responsibility, and exclude all liability (including under any implied warranties), for any matters arising out of or in connection with your reliance on the Information (including as to infringement of third party intellectual property rights) to the fullest extent permitted by law. Any Information concerning any possible use or application of Synthomer products is given by us in good faith; we do not warrant the fitness of any Synthomer products for any particular purpose and it is entirely for you to satisfy yourself fully as to the suitability of Synthomer products for any particular purpose. Synthomer products are sold in accordance with Synthomer's standard terms and conditions of sale which are available from [www.synthomer.com/tc](http://www.synthomer.com/tc).